

DESCRIPTION

Though modified bitumen membrane with APP (Polypropylene Atactic) and non-woven polyester mat which provides its high functionality characteristics. The top surface is available in ceramic granule and the bottom has a polyethylene finish. Besides providing a pleasing appearance, this granulated surface coating is designed to provide a long-lasting protection roof.

KEY TECHNOLOGY FEATURE

MODIFIED BITUMEN APP (ATACTIC POLYPROPILENE) MEMBRANES, POLYESTER REINFORSMENT.

PROPERTIES:

| Physical Property | Test Method (ASTM) | Value | |
|---|--------------------|--|--|
| ASPHALT MODIFIER | N/S | APP ATACTIC POLYPROPYLENE | |
| POLYESTER REINFORCEMENT | N/S | 0.0368 lb/sqft (180 gr/m2) | |
| Appearance | INTERNAL | ROLL | |
| Туре | INTERNAL | MODIFIED BITUMEN APP MEMBRANE | |
| Color | INTERNAL | WHITE, LIGHT BROWN, DARK BROWN, WEATHERWOOD, BUFF, SLATE, BLACK | |
| Elongation longitudinal, % | ASTM D-5147 | 45 | |
| Elongation transversal, % | ASTM D-5148 | 45 | |
| Tensile longitudinal Strength, N (lb/in2) | ASTM D-5147 | 400 (90) | |
| Tensile transversal Strength, N (lb/in2) | ASTM D-5148 | 294 (66) | |
| Low Temperature Flexibility (14.8 F, 9.6 C) | ASTM D-5147 | APPROVED | |
| POLYESTER REINFORCEMENT lb/sqft (gr/m2) | N/S | 0.0368 (180) | |
| Softening point min °F | ASTM D-36 | 284-293 | |
| Penetration 1/10 mm | ASTM D-5 | 22-24 | |
| Dimencional stability | ASTM D-5147 | Does not flow | |

ADVANTAGES

- Prevents / stopleaks
- Provides permanent waterprofing protection
- · Extends the life or your roof

• Due to its physical – chemical characteristics it provides excellent resistance, durability and elasticity

• To be used with high temperatures and/or low temperatures climates

• Waterproofing surfaces with resistance to thermal – structural medium movements

- It has excellent resistance to UV rays and to the mechanical action, as well as thermal shock
- · Excellent adhesion to any porus substrate
- High resistance to heat, cold chemicals, solvents, rain, snow and pollutants in the air
- Ponding water resistance

SUBSTRATES

- WOOD
- MOFIFIED BITUMEN MEMBRANES (SANDED OR SMOTH FINISH)
- ASPHALT BUILT-UP SURFACES
- CONCRETE
- POLYSOCYANURATE

APPLICATION TOOLS

Metallic trowel with rounded tip, regulated blowtorch, house and propane tank.

INSTALLATION PROCESS

PREPARATION

Roof need to be completly finisth to start working on the coating, slabs, parapets and other elements must be free of any mason-ry work, electrical & plumbing.

The surface must have a sizeable slope sufficiently to allow the evacuation of rainwater, at least 2%.

If any area that by their design tend to create hidden corners, diamonds should be made to draw water from these corners and redirect them to the general slope, these diamonds should have a minimum of 5%, starting at the top of the chamfer and ending at the level of the surface.

SURFACE PREPARATION

Surface must be clean, dry free of any grease or dirt. Pressure washing is recommended. Any existing coating must be removed by mechanical means such as wire brushing, sand blasting or scraping.

Scrape the surface to remove any adhered substance or mixture. The surface should be roughened to a depth of a minimum width of 2" in asphalt, or 4" in CONCRETE, less 8.0mm of the proposed waterproof roofing system.





Surface could have a rough finish if it allows the adherence of the roofing system and being careful by not leaving holes or bumps. A smooth surface it is not mandatory. The surface should be as smooth as possible to prevent ponding water

PRIMING AND REVIEW CRITICAL POINTS

Apply ASPHALT BASE PRIMER (ASTM D-41 type primer) by brush or roller. The usage of this primer improves the adhesion of the modified membranes.

In every corner, contractor should place reinforcements, these reinforcements are made depending on the size of the corner excelling at least 2" each side.

For chimneys or pipes, a part of at least the diameter of the flue or chimney (more 4") is cut into strips, 50% of it to cover the flue or chimney, the remaining material is melted against the slab. In domes, treat a banding strip type throughout faces covering at least 4" and 4" slab between the walls of the dome.

In drains do the procedure as follows, cut a part excelling at least 4" of each side of the downspout, cut an area in a tongue form and merge it with the drain (which can be PVC pipe, metal or concrete) and the remaining material is melted against the slab and parapet.

All these reinforcements are made with the THERMOTEK[™] USA PRO BASE SHEET.

COATING

Cut stickers and unroll on the roof. Wait until the rolls has flattened before proceeding. Align the rolls throughout the installation process. Proceed from the bottom of the roof and continue alignment fo the roll from the lowest part of the roof.

Mechanilly or Torch the BASE SHEET to the substrate ensuring proper allignment. If the base sheet is sanded, remove the excess of sand before your torch the cap sheet.

Cap sheet: Safely apply a torch to the poliethlyne surface. Warm the surface and continue to unroll while ensuring the torched area adheres to the substrate. Product performance can be impacted by inconsistent coverage with the torch. Be carefull not to torch to much o to little on the product because it will affect the performance.

Ensure a proper longitudinal overlapping on the rols, with a minimun of 4" on the sides and 6" on the end. To ensure proper adhesion on the seams, make a bleed through of 1/4" - 1" inch on every seam. On the transversal overlap lower the granule with a spatula and flame to improved adherance.

To finish the installation cover the bleed through on the overlapping with loose granule to have a good finish.

Its important that the installation has propoer distribution, ty to avoid seams that are at the same point, they need to be at least 24 inches on the end of each roll

YIELD

COVERAGE 100 sqft (NOMINAL)

PACKAGING

Roll

COLORS

GRAVEL: WHITE, LIGHT BROWN, DARK BROWN, WEATH-ERWOOD, BUFF, SLATE, BLACK

STORAGE

The product must be stored on a vertical position, never horizontal. Maximum load is two beds with a plywood between them. The roll must be handled with caution in order to not damage it and to avoid cutting or perforating the membrane. It must be stored on a closed place, to avoid their exposition to sunlight during long time periods.

SHELF LIFE

These products can be stores for a period of 2 years from its manufacture.

COMPLIANCES

- UL Classified 790 Fire Resistance Class A
- UL Classified 1890 Up Lift Resistance
- NRCA National Roofing Contractor asociation Member
- TDI Texas Departament of Insurance Evaluation ID RC-464





APPLICATION (WHERE THESE PRODUCTS ARES USED - PHYSICAL PLACE)

THERMOTEK[™] USA PRO POLYESTER TORCH is an ideal product for use over porus surfaces. It can be used over many different types of roofing systems.

MAINTENANCE / CLEAN UP

This Modified asphalts system requires cleaning every three months using detergent (such as TSP or TSP substitute) and water only. Clean application tools and equipment with 100% Pure Mineral Spirit.

FOR BEST PERFORMANCE

Should not be applied at temperatures below $40^{\circ}F$ (4.5°C) or if rain is expected within 1 to 4 hours after the application.

Do not apply on wet surfaces

Do not use in swimming pools or other submerged conditions where the sealant will be exposed to strong oxidizers.

It is not for continuous traffic. Do not use in areas of storage of solvents or gases.

| APPROVALS | AND CERT | IFICATIONS |
|------------------|----------|-------------------|
|------------------|----------|-------------------|



| Product Specifications | | | | | | | | |
|------------------------|-----------------------|-------------|------------|---------------------|------|-------------|--|--|
| Roll Thickness | Roll Size | Roll Length | Roll Width | Approx. Roll Weight | Mils | Yield | | |
| 3.5 mm | 1 SQ (107,61 sqft) | 32,80 ft | 3,281 ft | 83.75 lbs | 140 | 93,646 sqft | | |
| 4.0 mm | 1 SQ (107,61 sqft) | 32,80 ft | 3,281 ft | 97.93 lbs | 160 | 93,646 sqft | | |
| 4.5 mm | 1 SQ (107,61 sqft) | 32,80 ft | 3.281 ft | 108.78 lbs | 180 | 93,646 sqft | | |
| 5.0 mm | 1 SQ (107,61 sqft) | 32,80 ft | 3.281 ft | 120.15 lbs | 200 | 93,646 sqft | | |

We as THERMOTEK GROUP guarantee that since our products are shipped from the production plant they will be free of manufacturing defects; all the recommendations contained herein follow tests we consider as reliable and are subject to change without prior notice. THERMOTEK GROUP does not assume any responsibility for coverage, performance on injuries resulting from storage, handling or use of our products. Liability, if any, is limited to product replacement, to the terms stated within the executed warranty.

